



AFT INTERNATIONAL N.V.  
 TER STRATENWEG 50  
 BE-2520 OELEGEM  
 Tel. +32/3.475.93.03  
 info@aft-international.be

Datasheet; Neosport 2,1 mm en 3,2 mm zwart

Property/ Article	1400 Continue CR for medical field	CR Sponge	CS Sponge	SBR Sponge
Elongation, Break (%) (min)		266	350	300
Tensile Strength (kg/ sg. cm) (min)	4.55	13.9	5.07	5.0
Tear Strength (kg/ sg. cm) (min)	2.85	4.05	1.64	2
Hardness (Type C)		4-6 degrees	4-6/ 6-8 degrees	6-8 degrees
Density (G/ cubic cm.)		0.26-0.27	0.16-0.18	0.2+/- 0.02
Modulus at 200% Elongation (kg/ sq. cm.)		2-3	2-3	4-5
Water Absorption By Weight (%) (max)	1	1	1	1
Shrinkage (70 degrees C., 24 hrs.) (max)	2	2	2	2
Compression Set (Compressed 50%,25 degrees C)	10.08%	15-25	15-25 5.94%	15-25
Compressed Deflection test (kgf/ cm)	0.26		0.20	

All of our products meet high quality standards; the dyes and neoprene material are both tested to ensure safety standards.